

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 826 714 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

04.03.1998 Bulletin 1998/10

(51) Int. Cl.⁵: **C08G 65/00**, C09D 171/02,

B01D 12/00

(21) Application number: **97114418.3**(22) Date of filing: **21.08.1997**

(84) Designated Contracting States:

**AT BE CH DE DK ES FI FR GB GR IE IT LI LU MC
NL PT SE**(30) Priority: **26.08.1996 IT MI961785**(71) Applicant: **Ausimont S.p.A.****20121 Milano (IT)**

(72) Inventors:

- **Strepparola, Ezio**
Treviglio, Bergamo (IT)

- **Fontana, Simonetta**

Milano (IT)

- **Silvani, Rossella**

Lentate sul Seveso, Milano (IT)

(74) Representative:

Sama, Daniele, Dr. et al**Sama Patents,****Via G.B. Morgagni, 2****20129 Milano (IT)**(54) **Method for the removal of water from surfaces**

(57) Method for the water removal from a surface, which comprises covering the surface with a composition having specific weight higher than that of the water, and subsequently removing water from the composition by skimming, such composition comprising a (per)fluoropolyether having molecular weight comprised between 300 and 1500 and a non ionic additive having a (per)fluoropolyetheral structure similar to that of the solvent, linked to an hydrogenated part of hydrophilic type, the molecular weight of the (per)fluorinated part is comprised between 400 and 1200 and the ratio by weight between (per)fluorinated part and hydrogenated part is comprised between 1.5 and 3.5.

EP 0 826 714 A2

Description

The present invention relates to a method for removing water from various surfaces. The problem of the water removal from processed materials is particularly felt in the electronics and fine mechanics field.

One of the most used methods (US-A-4,491,531) consisted in the use of CFC (chlorofluorocarbons) mixtures and of an additive chosen from the following classes: diamines salts, mono- or diesters of the phosphoric acid or mixtures thereof. Such mixtures allowed the water removal from the material surface by skimming.

The banning of the CFC use made it necessary the research of alternative mixtures which, even though maintaining the effectiveness shown by CFC, had a lower environmental impact.

US-A-5,125,978 claims the utilization of mixtures comprising a perfluorinated solvent and a non ionic additive. Such mixtures require an amount of additive not lower than 0.1%, generally higher, and the obtained water removal is not always complete. Moreover the boiling temperature of the solvent, usually around 60°C, makes unavoidable remarkable losses of solvent in the environment.

The Applicant has surprisingly found that mixtures formed by a (per)fluoropolyether and by extremely low amounts of a non ionic additive result particularly effective in the water removal from various surfaces.

The employment of very low amounts of additive, also of 0.03% by weight, makes it easier the complete removal of the residues of the additive from the treated surface.

The present invention relates moreover to a method for the water removal from a surface, which method comprises covering the surface with a composition having specific weight higher than that of the water, and subsequently removing water from the composition by skimming, such composition being formed by a (per)fluoropolyether having molecular weight comprised between 300 and 1500 and by a non ionic additive having a structure such as:



with $L = X-CH_2CH_2(OCH_2CH_2)_nB$
 wherein $X = CH_2O$; CH_2NR'' ; $CONR''$;
 $CH_2OCH_2CH_2NR''$; CH_2OCOCH_2O
 wherein n is such that satisfies the parameter K defined below

$B = OH$; SH ; NHR'' ; OCH_3 ; $OCOCH_3$.

with $R'' = H$; alkyl C_{1-3} .

$Y = CF_3$ or F

The R_f radical of (per)fluoropolyether type comprises repeating units randomly distributed along the chain of the polymer chosen from:

(CF_2CF_2O) , $(CFYO)$ wherein Y is equal to F or CF_3 , (C_3F_6O) , $(CF_2(CF_2)_2O)$ wherein z is an integer equal to 2 or 3, $(CF_2CF(OR_f)O)$, $(CF(OR_f)O)$ wherein R_f is equal to $-CF_3$, $-C_2F_5$, $-C_3F_7$; $CR_4R_5CF_2CF_2O$ wherein R_4 and R_5 are equal to or different from each other and are chosen from H, Cl or perfluoroalkyl, for instance with 1-4 C atoms.

When the additive is of formula (I), the T terminal of the perfluoropolyether radical is chosen from $-CF_3$, $-C_2F_5$, $-C_3F_7$, $ClCF_2CF(CF_3)-$, $CF_3CFClCF_2-$, $ClCF_2CF_2-$, $ClCF_2-$.

The number average molecular weight of the (per)fluoroetheral part ($T-OR_f$ or $CF_3R_fCF_2$) is comprised between 500 and 1200 and the ratio by weight (K) between (per)fluorinated part and hydrogenated part is comprised between 1.5 and 3.5. Indeed if the ratio is lower than 1.5 it prevails the contribution of the hydrophilic hydrogenated part and the additive tends to be water-soluble and therefore extracted from the aqueous phase. If the ratio is higher than 3.5 the additive is ineffective in the water removal. In the case of the formulae (I) and (II) such ratio K corresponds respectively to $T-OR_f(CFY)/L$ and $CF_2OR_fCF_2/2L$.

In particular the following fluoropolyetheral R_f can be mentioned as preferred:

(a) $-(CF_2CF(CF_3)O)_a(CFYO)_b-$

wherein Y is F or CF_3 ; a and b are integers such that the molecular weight is comprised in the range indicated above;

a/b is comprised between 10 and 100;

or the repeating units indicated in (a) can be bound as follows:

$-(CF_2CF(CF_3)O)_a(CFYO)_b-CF_2(R')_xCF_2O-$

$(CF_2CF(CF_3)O)_a(CFYO)_b-$

wherein R' is a fluoroalkylenic group, for instance from 1 to 4 C;

(b) $-(CF_2CF_2O)_c(CF_2O)_d(CF_2(CF_2)_2O)_h-$

wherein c, d and h are integers such that the molecular weight is comprised in the range indicated above; c/d is comprised between 0.1 and 10; h/(c+d) is comprised between 0 and 0.05, z has the value indicated above, h can also be equal to 0

(c) $-(CF_2CF(CF_3)O)_e(CF_2CF_2O)_f(CFYO)_g-$ wherein Y is F or CF_3 ; e, f, g are integers such that the molecular weight is comprised in the range indicated above; e/(f+g) is comprised between 0.1 and 10, f/g is comprised between 2 and 10,

(d) $-(CF_2O)_j(CF_2CF(OR_f)O)_k(CF(OR_f)O)_l-$

wherein $R_f = -CF_3$, $-C_2F_5$, $-C_3F_7$; j, k, l are integers such that the molecular weight is comprised in the range indicated above; k+l and j+k+l are at least equal to 2, k/(j+l) is comprised between 0.01 and 1000, l/j is comprised between 0.01 and 100;


(e) $-(CF_2(CF_2)_2O)_z-$

wherein z is an integer such as to give the molecular weight indicated above, z has the meaning


already defined;





wherein R_4 and R_5 are equal to or different from each other and are chosen from H, Cl or perfluoroalkyl, for instance with 1-4 C atoms, j being an integer such that the molecular weight is that indicated above; said unit inside the fluoropolyoxyalkylenic chain being linked each other as follows:



wherein R_1 is a fluoroalkylenic group, for instance from 1 to 4 C, p and q are integers such that the molecular weight is that indicated above;



j being an integer such as to give the molecular weight indicated above; said units being linked each other inside the fluoropolyoxyalkylenic chain as follows to have a bivalent radical:



wherein R_1 has the meaning indicated above, x is 0 or 1, a and b are integers and $a+b$ is at least 1 and such that the molecular weight is that indicated above.

These structures comprising the repeating units indicated and the methods for preparing them are described in the patents GB 1,104,482, USP 3,242,218, USP 3,665,041, USP 3,715,378, USP 3,665,041, EP 148,482, USP 4,523,039, USP 5,144,092, and as to functional derivatives see USP 3,810,874. All these patents are incorporated herein by reference.

The (per)fluoropolyether according to the present invention has number average molecular weight M_n comprised between 300 and 1500, preferably between 400 and 800, and is preferably a perfluoropolyether.

The (per)fluoropolyether has preferably structure of the type:




wherein R_1 has the meaning indicated above and T' is selected from $-CF_3$, $-C_2F_5$, $-C_3F_7$; T'' is selected from $-CF_3$, $-C_2F_5$, $-C_3F_7$, $-CF_2H$, $-CFHCF_3$, CF_2CF_2H .

Particularly preferred structures are the following:



a and b are integers such that the molecular weight is within the range indicated by a''/b'' comprised between 1 and 40; T' and T'' are as defined above.



p and q are integers such that the molecular weight is within the range indicated by p/q comprised between 0.6 and 1.2; T' and T'' are as defined above.



wherein s' is an integer such that the molecular weight is within the range indicated; T' and T'' are as defined above.

The extreme effectiveness of these compositions allows the use of amounts of additive generally lower or equal to 0.1% by weight, preferably lower than 0.05%.

For the preparation process of the additives, the above mentioned patents can be utilized, for instance by starting from a monofunctional or bifunctional (per)fluoropolyether, i.e. having $-COF$ terminals, according to USP 3,810,874, incorporated herein by reference.

For instance for the preparation of additives wherein $X=CH_2O$ and $B=OH$ one starts from the product having $-COF$ terminals. The $-COF$ group is reduced with metal hydrides to give the alcoholic derivative $-CH_2OH$ which by treatment with 1 mole of ethylene oxide gives the monoaddition product $-CH_2O-CH_2CH_2OH$. The corresponding tosyl derivative is prepared by reaction with the paratoluenesulphonic acid chloride. The tosyl derivative is then reacted with a large excess of monocomponent polyethyleneglycol in the presence of potassium tertbutylate. For the other bridge bonds X , the teaching of the above mentioned USP 3,810,874 is followed.

Experimental part

The used (perfluoropolyetheral) solvents are commercially available and differ by number average molecular weight and, consequently, by boiling point and viscosity.

The water removal was measured according to the following methodology:


a drop of distilled water (about 0.1 ml) is deposited on a flat surface of a glass crystallization vessel with base area of about 10 cm^2 . Some ml of the solution under examination containing 0.03% by weight of additive are then added along the walls until covering the drop and it is noticed what happens after 30". The assigned points correspond to the following cases:

- 1 complete removal
- 2 Residue <10%
- 3 Residue >10%
- 4 No removal

The values 1 and 2 are considered satisfactory.

The following examples are given only for illustrative purposes and are not limitative of the present invention.

EXAMPLE 1



moles) are dropped in a more necks jacketed reactor, equipped with thermocouple, mechanical stirrer and reflux, containing 300 g of 50% aqueous solution of NaOH and 200 g (1 mole) of the paratoluensulphonic acid chloride dissolved in 800 ml of CH_2Cl_2 . It is left under strong stirring for 8 hours at room temperature and after having added 1 l of water it is left under stirring for further 4 hours.

It is brought to neutrality with hydrochloric acid and the organic phase is separated. After distillation of the solvent, 746 g of tosyl derivative are obtained which appears as a lipid liquid, characterized by IR, ^{19}F NMR and ^1H NMR.

105 g (0.12 moles) of the tosyl derivative prepared above are dropped at 60°C in 4 hours in a more necks jacketed reactor, equipped with thermocouple, mechanical stirrer and reflux, containing 15.6 g (0.14 moles) of potassiumterbutylate and 120 g (0.6 moles) of tetraethyleneglycol. Then it is acidified with diluted hydrochloric acid and the organic phase is separated. After a second washing with 150 ml of 5% chloridric acid the organic phase brought to dryness results to be constituted by 101 g of $\text{CF}_3\text{O}(\text{C}_3\text{F}_6\text{O})_3(\text{CF}_2\text{O})_{0.2}\text{CF}_2\text{CH}_2\text{OCH}_2\text{CH}_2(\text{OCH}_2\text{CH}_2)_2\text{OH}$, characterized by IR, ^{19}F NMR and ^1H NMR. This compound is characterized by $\text{K}=2.6$.

A 0.03% solution of $\text{CF}_3\text{O}(\text{C}_3\text{F}_6\text{O})_3(\text{CF}_2\text{O})_{0.2}\text{CF}_2\text{CH}_2\text{OCH}_2\text{CH}_2(\text{OCH}_2\text{CH}_2)_2\text{OH}$ in $\text{CF}_3\text{O}(\text{C}_3\text{F}_6\text{O})_{1.7}(\text{CF}_2\text{O})_{0.1}\text{CF}_3$, tested according to the method described above, obtains 1 as evaluation.

ESSEMPIO 2

105 g (0.12 moles) of the tosyl derivative prepared as indicated in Example 1 are dropped at 60°C in 4 hours in a more necks jacketed reactor, equipped with thermocouple, mechanical stirrer and reflux, containing 15.6 g (0.14 moles) of potassiumterbutylate and 143 g (0.6 moles) of pentaethyleneglycol. Then it is acidified with diluted hydrochloric acid and the organic phase is separated. After a second washing with 250 ml of 5% hydrochloric acid the organic phase brought to dryness results to be constituted by 103 g of $\text{CF}_3\text{O}(\text{C}_3\text{F}_6\text{O})_3(\text{CF}_2\text{O})_{0.2}\text{CF}_2\text{CH}_2\text{OCH}_2\text{CH}_2(\text{OCH}_2\text{CH}_2)_5\text{OH}$, characterized by IR, ^{19}F NMR and ^1H NMR. This compound is characterized by $\text{K}=2.2$.

A 0.03% solution of $\text{CF}_3\text{O}(\text{C}_3\text{F}_6\text{O})_3(\text{CF}_2\text{O})_{0.2}\text{CF}_2\text{CH}_2\text{OCH}_2\text{CH}_2(\text{OCH}_2\text{CH}_2)_5\text{OH}$ in $\text{CF}_3\text{O}(\text{C}_3\text{F}_6\text{O})_{1.7}(\text{CF}_2\text{O})_{0.1}\text{CF}_3$, tested according to the method described above, obtains 1 as evaluation.

EXAMPLE 3 (comparative)

In a more necks jacketed reactor, equipped with thermocouple, mechanical stirrer and reflux containing 15.6 g (0.14 moles) of potassiumterbutylate and 63.6 g

(0.6 moles) of diethyleneglycol, 105 g (0.12 moles) of the tosyl derivative prepared as indicated in Example 1 are dropped at 60°C in 4 hours. Then it is acidified with diluted hydrochloric acid and the organic phase is separated. After a second washing with 100 ml of 5% hydrochloric acid the organic phase brought to dryness results to be constituted by 93 g of $\text{CF}_3\text{O}(\text{C}_3\text{F}_6\text{O})_3(\text{CF}_2\text{O})_{0.2}\text{CF}_2\text{CH}_2\text{OCH}_2\text{CH}_2(\text{OCH}_2\text{CH}_2)_2\text{OH}$, characterized by IR, ^{19}F NMR and ^1H NMR. The product is characterized by $\text{K}=4.0$.

A 0.03% solution of $\text{CF}_3\text{O}(\text{C}_3\text{F}_6\text{O})_3(\text{CF}_2\text{O})_{0.2}\text{CF}_2\text{CH}_2\text{OCH}_2\text{CH}_2(\text{OCH}_2\text{CH}_2)_2\text{OH}$ in $\text{CF}_3\text{O}(\text{C}_3\text{F}_6\text{O})_{1.7}(\text{CF}_2\text{O})_{0.1}\text{CF}_3$, tested according to the method described above, obtains 3 as evaluation.

EXAMPLE 4

In a more necks jacketed reactor, equipped with thermocouple, mechanical stirrer and reflux, containing 53.8 g (0.06 moles) of $\text{CF}_3\text{O}(\text{C}_3\text{F}_6\text{O})_3(\text{CF}_2\text{O})_{0.2}\text{CF}_2\text{CH}_2\text{OCH}_2\text{CH}_2(\text{OCH}_2\text{CH}_2)_4\text{OH}$, 6.72 g (0.06 moles) of potassiumterbutylate are added and left under vigorous stirring until the complete disappearance of the solid. Then the terbutylic alcohol developed is removed by distillation, 10 g (0.07 moles) of methyl iodide are dropped and left under stirring for 4 hours.

After addition of 300 ml of water to dissolve the formed potassium iodide, the organic phase, separated and dried under vacuum, is constituted by 53 g of $\text{CF}_3\text{O}(\text{C}_3\text{F}_6\text{O})_3(\text{CF}_2\text{O})_{0.2}\text{CF}_2\text{CH}_2\text{OCH}_2\text{CH}_2(\text{OCH}_2\text{CH}_2)_4\text{OMe}$, characterized by IR, ^{19}F NMR and ^1H NMR. The compound is characterized by $\text{K}=2.4$.

A 0.03% solution of $\text{CF}_3\text{O}(\text{C}_3\text{F}_6\text{O})_3(\text{CF}_2\text{O})_{0.2}\text{CF}_2\text{CH}_2\text{OCH}_2\text{CH}_2(\text{OCH}_2\text{CH}_2)_4\text{OMe}$ in $\text{CF}_3\text{O}(\text{C}_3\text{F}_6\text{O})_{1.7}(\text{CF}_2\text{O})_{0.1}\text{CF}_3$ tested as described above obtains 2 as evaluation.

EXAMPLE 5 (comparative)

In a more necks jacketed reactor, equipped with thermocouple, mechanical stirrer and reflux, containing 48.5 g (0.06 moles) of $\text{CF}_3\text{O}(\text{C}_3\text{F}_6\text{O})_3(\text{CF}_2\text{O})_{0.2}\text{CF}_2\text{CH}_2\text{OCH}_2\text{CH}_2(\text{OCH}_2\text{CH}_2)_2\text{OH}$, 6.72 g (0.06 moles) of potassium terbutylate are added and left under vigorous stirring until the complete disappearance of the solid. Then the terbutylic alcohol developed is removed by distillation, 10 g (0.07 moles) of methyl iodide are dropped and left under stirring for 4 hours.

After addition of 300 ml of water to dissolve the formed potassium iodide, the organic phase, separated and dried under vacuum, is formed by 47 g of $\text{CF}_3\text{O}(\text{C}_3\text{F}_6\text{O})_3(\text{CF}_2\text{O})_{0.2}\text{CF}_2\text{CH}_2\text{OCH}_2\text{CH}_2(\text{OCH}_2\text{CH}_2)_2\text{OMe}$, characterized by IR, ^{19}F NMR, and ^1H NMR. The

product is characterized by $K=3.6$. A 0.03% solution of $CF_3O(C_3F_6O)_3(CF_2O)_{0.2}CF_2CH_2OCH_2CH_2(OCH_2CH_2)_2OMe$ in $CF_3O(C_3F_6O)_{1.7}(CF_2O)_{0.1}CF_3$ tested as described before obtains 3 as evaluation.

EXAMPLE 6

In a more necks jacketed reactor, equipped with thermocouple, mechanical stirrer and reflux, containing 27 g (0.03 moles) of $CF_3O(C_3F_6O)_3(CF_2O)_{0.2}CF_2CH_2OCH_2CH_2(OCH_2CH_2)_4OH$, 3.36 g (0.03 moles) of potassiumterbutylate are added and left under vigorous stirring until the complete disappearance of the solid. Then 5.5 g (0.07 moles) of the chloride of the acetic acid are dropped and left under stirring for 2 hours. After addition of 100 ml of water the organic phase, separated and anhydried under vacuum is formed by 27.6 g of $CF_3O(C_3F_6O)_3(CF_2O)_{0.2}CF_2CH_2OCH_2CH_2(OCH_2CH_2)_4OCOMe$, characterized by IR, ^{19}F NMR, and H NMR. The compound is characterized by $K=2.2$.

A 0.03% solution of $CF_3O(C_3F_6O)_3(CF_2O)_{0.2}CF_2CH_2OCH_2CH_2(OCH_2CH_2)_4OCOMe$ in $CF_3O(C_3F_6O)_{1.7}(CF_2O)_{0.1}CF_3$ tested as described before obtains 2 as evaluation.

EXAMPLE 7 (comparative)

In a more necks jacketed reactor, equipped with thermocouple, mechanical stirrer and reflux, containing 35 g (0.05 moles) of $CF_3O(C_3F_6O)_3(CF_2O)_{0.2}CF_2COOCH_3$, 4.3 g (0.07 moles) of ethanolamine are added and are left under vigorous stirring for 3 hours. After addition of 100 ml of 3% hydrochloric acid, the organic phase, separated and anhydried under vacuum, is formed by 35.66 g of $CF_3O(C_3F_6O)_3(CF_2O)_{0.2}CF_2CONHCH_2CH_2OH$, characterized by IR, ^{19}F NMR, and H NMR. The product is characterized by $K=7.3$.

A 0.03% solution of $CF_3O(C_3F_6O)_3(CF_2O)_{0.2}CF_2CONHCH_2CH_2OH$ in $CF_3O(C_3F_6O)_{1.7}(CF_2O)_{0.1}CF_3$ tested as described before obtains 4 as evaluation.

EXAMPLE 8

A 0.03% solution of $CF_3O(C_3F_6O)_3(CF_2O)_{0.2}CF_2CH_2OCH_2CH_2(OCH_2CH_2)_5OH$ (having $K=2.2$) in $CF_3O(C_3F_6O)_{2.5}(CF_2O)_{0.1}CF_3$ tested as described before obtains 1 as evaluation.

EXAMPLE 9 (comparative)

A 0.03% solution of

$CF_3O(C_3F_6O)_3(CF_2O)_{0.2}CF_2CH_2OCH_2CH_2OH$ (having $K=8.6$) in $CF_3O(C_3F_6O)_{1.7}(CF_2O)_{0.1}CF_3$ tested as described before obtains 4 as evaluation.

EXAMPLE 10 (comparative)

A 0.03% of $CF_3O(C_3F_6O)_3(CF_2O)_{0.2}CF_2CH_2OH$ (having $K=20.8$) in $CF_3O(C_3F_6O)_{2.5}(CF_2O)_{0.1}CF_3$ tested as described before obtains 4 as evaluation.

Claims

1. Method for the removal of water from a surface, which method comprises covering the surface with a composition having specific weight higher than that of the water, and subsequently removing water from the composition by skimming, such composition comprising a (per)fluoropolyether having molecular weight comprised between 300 and 1500 and a non ionic additive having a structure such as:



with $L = X-CH_2CH_2(OCH_2CH_2)_nB$

wherein $X = CH_2O$; CH_2NR'' ; $CONR''$; $CH_2OCH_2CH_2NR''$; CH_2OCOCH_2O

wherein n is such that satisfies the parameter K defined below,

$B = OH$; SH ; NHR'' ; OCH_3 ; $OCOCH_3$.

with $R'' = H$; alkyl C_{1-3}

$Y = CF_3$ or F

wherein the R_i radical of (per)fluoropolyetheral type comprises repeating units randomly distributed along the chain of the polymer chosen from: (CF_2CF_2O) , $(CFYO)$ wherein Y is equal to F or CF_3 , (C_3F_6O) , $(CF_2(CF_2)_2O)$ wherein z is an integer equal to 2 or 3, $(CF_2CF(OR_i)O)$, $(CF(OR_i)O)$ wherein R_i is equal to $-CF_3$, $-C_2F_5$, $-C_3F_7$; $CR_4R_5CF_2CF_2O$ wherein R_4 and R_5 are equal to or different from each other and are chosen from H , Cl or perfluoroalkyl, for instance with 1-4 C atoms, the T terminal of the perfluoropolyetheral radical is chosen from $-CF_3$, $-C_2F_5$, $-C_3F_7$, $ClCF_2CF(CF_3)-$, $CF_3CFClCF_2-$, $ClCF_2CF_2-$, $ClCF_2-$, the number average molecular weight of the (per)fluoroetheral part ($T-OR_i$ or $CF_2R_iCF_2$) is comprised between 500 and 1200 and the ratio by weight (K) between (per)fluorinated part and hydrogenated part is comprised between 1.5 and 3.5.

2. Method according to claim 1 wherein the R_i group comprises the following repeating units:

(a) $-(CF_2CF(CF_3)O)_a(CFYO)_b-$
wherein Y is F or CF_3 ; a and b are integers
such that the molecular weight is comprised in
the range indicated above; a/b is comprised
between 10 and 100; or the repeating units
indicated in (a) can be bound as follows:

$-(CF_2CF(CF_3)O)_a(CFYO)_b-CF_2(R'_1)_xCF_2-O-$
 $(CF_2CF(CF_3)O)_a(CFYO)_b-$
wherein R'_1 is a fluoroalkylenic group, for
instance from 1 to 4 C;

(b) $-(CF_2CF_2O)_c(CF_2O)_d(CF_2(CF_2)_2O)_h-$
wherein c, d and h are integers such that the
molecular weight is comprised in the range
indicated above; c/d is comprised between 0.1
and 10; h/(c+d) is comprised between 0 and
0.05, z has the value indicated above, h can
also be equal to 0

(c) $-(CF_2CF(CF_3)O)_e(CF_2CF_2O)_f(CFYO)_g-$
wherein Y is F or CF_3 ; e, f, g are integers such
that the molecular weight is comprised in the
range indicated above; e/(f+g) is comprised
between 0.1 and 10, f/g is comprised between
2 and 10,

(d) $-(CF_2O)_j(CF_2CF(OR_r))_k(CF(OR_r))_l-$
wherein R_r is $-CF_3$, $-C_2F_5$, $-C_3F_7$; j, k, l are inte-
gers such that the molecular weight is com-
prised in the range indicated above; k+l and
j+k+l are at least equal to 2, k/(j+l) is comprised
between 0.01 and 1000, l/j is comprised
between 0.01 and 100;

(e) $-(CF_2(CF_2)_zO)_s-$
wherein s is an integer such as to give the
molecular weight indicated above, z has the
meaning already defined;

(f) $-(CR_4R_5CF_2CF_2O)_i-$
wherein R_4 and R_5 are equal to or different
from each other and are chosen from H, Cl or
perfluoroalkyl, for instance with 1-4 C atoms, i
being an integer such that the molecular weight
is that indicated above; said units inside the
fluoropolyoxyalkylenic chain being linked
each other as follows:

$-(CR_4R_5CF_2CF_2O)_p-R'_1-O-$
 $(CR_4R_5CF_2CF_2O)_q-$
wherein R'_1 is a fluoroalkylenic group, for
instance from 1 to 4 C, p' and q' are integers
such that the molecular weight is that indicated
above;

(g) $-(CF(CF_3)CF_2O)_j-$
j' being an integer such as to give the molecu-
lar weight indicated above; said units being
linked each other inside the fluoropolyoxy-
alkylenic chain as follows to have a bivalent
radical:

$-(CF_2CF(CF_3)O)_a-CF_2(R'_1)_xCF_2-O-$
 $(CF(CF_3)CF_2O)_b-$


wherein R'_1 has the meaning indicated above, x
is 0 or 1, a' and b' are integers and a'+b' is at

least 1 and such that the molecular weight is
that indicated above.


3. Method according to claims 1 or 2 wherein the addi-
tive has the structure of type (I) and molecular
weight of the perfluorinated part comprised
between 500 and 1000.

4. Method according to claims 1 or 2 wherein the addi-
tive is of type (II) and the molecular weight of the
perfluorinated part is comprised between 800 and
1200.

5. Method according to claim 2 wherein the perfluor-
opolyether belongs to one of the following classes:



wherein a' and b' are integers such that the molecu-
lar weight is within the range indicated with a'/b'
comprised between 1 and 40; T' is $-CF_3$, $-C_2F_5$, $-$
 C_3F_7 ; T' is equal to T' or $-CF_2H$, $-CF_2CF_2H$, $-$
 $CFHCF_3$, as defined above;



p and q are integers such that the molecular weight
is within the range indicated with p/q comprised
between 0.6 and 1.2; T' and T'' are as defined
above;



wherein s' is an integer such that the molecular
weight is within the indicated range; T' and T'' are as
defined above.

6. Method according to claim 1, wherein the solvent is
selected from $CF_3O(C_3F_6O)_1$, $\gamma(CF_2O)_0.1CF_3$ and
 $CF_3O(C_3F_6O)_{2.5}(CF_2O)_{0.1}CF_3$ and the additive has
the formula
 $CF_3O(C_3F_6O)_3(CF_2O)_{0.2}CF_2CH_2OCH_2CH_2(OCH_2$
 $CH_2)_nOH$ with n=4 or 5.

7. Method according to claims 1-6 wherein the
amount of surfactant in the composition is lower
than or equal to 0.1% by weight.

8. Additives according to anyone of the preceding
claims.

9. Use of a composition according to claims 1-7 for the
removal of water from a surface.

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 826 714 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:

18.11.1998 Bulletin 1998/47

(51) Int. Cl.⁶: C08G 65/00, C09D 171/02,

B01D 12/00, C08G 65/32

(43) Date of publication A2:

04.03.1998 Bulletin 1998/10

(21) Application number: 97114418.3

(22) Date of filing: 21.08.1997

(84) Designated Contracting States:

AT BE CH DE DK ES FI FR GB GR IE IT LI LU MC
NL PT SE

(30) Priority: 26.08.1996 IT MI961785

(71) Applicant: Ausimont S.p.A.

20121 Milano (IT)

(72) Inventors:

- Strepparola, Ezio
Treviglio, Bergamo (IT)

- Fontana, Simonetta

Milano (IT)

- Silvani, Rossella

Lentate sul Seveso, Milano (IT)

(74) Representative:

Sama, Daniele, Dr. et al

Sama Patents,

Via G.B. Morgagni, 2

20129 Milano (IT)

(54) Method for the removal of water from surfaces

(57) Method for the water removal from a surface, which comprises covering the surface with a composition having specific weight higher than that of the water, and subsequently removing water from the composition by skimming, such composition comprising a (per)fluoropolyether having molecular weight comprised between 300 and 1500 and a non ionic additive having a (per)fluoropolyetheral structure similar to that of the solvent, linked to an hydrogenated part of hydrophilic type, the molecular weight of the (per)fluorinated part is comprised between 400 and 1200 and the ratio by weight between (per)fluorinated part and hydrogenated part is comprised between 1.5 and 3.5.

EP 0 826 714 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 97 11 4418

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
X	SIMEONE G ET AL: "FUNDAMENTAL PROPERTIES OF FLUOROPOLYETHER-BASED RESINS AND RELATED COATINGS" ANGEWANDTE MAKROMOLEKULARE CHEMIE, vol. 236, 1 March 1996, pages 111-127, XP000581594 * page 113: table 1 *	8	C08G65/00 C09D171/02 B01D12/00 C08G65/32
A	DATABASE WP1 Section Ch. Week 9438 Derwent Publications Ltd., London, GB: Class A97, AN 94-305368 XP002075127 & JP 06 210 103 A (SHIMADA RIKI KOGYO KK) * abstract *	1-9	
A	PATENT ABSTRACTS OF JAPAN vol. 096, no. 005, 31 May 1996 & JP 08 024504 A (DU PONT MITSUI FLUOROCHEM CO LTD), 30 January 1996 * abstract *	1-9	
A.D	EP 0 509 739 A (MINNESOTA MINING & MFG) 21 October 1992 * claims 1.10.12 *	1-9	TECHNICAL FIELDS SEARCHED (Int.Cl.6) C08G B01D
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 20 August 1998	Examiner O'Sullivan, T
CATEGORY OF CITED DOCUMENTS		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons A : technological background & : member of the same patent family, corresponding document P : intermediate document X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category	

EPO FORM 1503 (01.01.96)